

Description:

Creator 2 side coated woodfree paper with high gloss and excellent properties.

This Creator brand gloss paper has multiple features to ensure optimal print quality: high whiteness, very good paper and ink gloss, excellent dot transfer, and high runnability.

Available in a wide range of substances and formats, in sheets and reels.

End uses:

Books, Brochures, Catalogues, Covers, Direct mail, Folders, Inserts, Packaging, Postcards

Print methods:

Flexo, Laser/Dry toner, Offset, Rotogravure

Certificates:

- [Elemental Chlorine Free \(ECF\) - Coated paper](#)
- [Declaration of Biodegradability \(EN 13432-2000\) - Coated paper](#)
- [Printed Paper Optical Properties \(DIN ISO 12647-2\)- Coated Gloss](#)
- [Hazardous Substances in Electrical and Electronic Equipment \(RoHS\) - Coated Gloss](#)
- [Sensory Analysis \(EN 1230\) - Coated Gloss](#)
- [Safety of Toys \(EN 71-3\) - Coated Gloss](#)
- [Packaging and Packaging Waste \(EN 13427\) - Coated Gloss](#)
- [FSC Chain of Custody \(multisite\)](#)
- [PEFC Chain of Custody \(multisite\)](#)
- [EMAS Motril mill](#)
- [EMAS Sant Joan](#)
- [EMAS Zaragoza mill](#)
- [ISO 14001 Environment](#)
- [ISO 50001 Energy Efficiency](#)
- [ISO 9001 Quality](#)
- [ISO 45001 Health and Safety](#)

Technical specifications

Property	Test Method	Unit	Tolerance	Tolerance															
				90	100	115	125	130	135	150	170	200	225	250	270	300	350	380	
Substance	ISO 536 TAPPI T410	g/m ²	±4%	90	100	115	125	130	135	150	170	200	225	250	270	300	350	380	
Thickness	ISO 534 TAPPI T411	µm	±4%	67	75	85	91	95	99	110	125	146	166	186	202	230	278	302	
Opacity	ISO 2471 TAPPI T519	%	-2.0	90	91	93.5	93.5	95.0	95.5	96.5	97.0	-	-	-	-	-	-	-	
Brightness R457/D65	ISO 2470-2	%	±2	95.2	95.2	95.2	95.2	95.2	95.2	95.2	95.2	95.2	95.2	95.2	95.2	95.2	95.2	95.2	
Whiteness D65/10°	ISO 11475	CIE	±3	119.0	119.0	119.0	119.0	119.0	119.0	119.0	119.0	119.0	119.0	119.0	119.0	119.0	119.0	119.0	
Paper gloss	ISO 8254-1 TAPPI T480	%	±5	70	70	70	70	70	70	70	72	72	72	72	72	72	72	72	
Bekk smoothness	ISO 5627 TAPPI T479	s	±30%	1400	1100	950	1500	1450	1400	1300	1000	800	700	600	500	400	300	200	
Relative humidity	TAPPI T502	%	±7	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	

Storage recommendations

Ideally, the paper should be stocked in pressrooms conditioned to 50% (±5) relative humidity and 23°C (±2) temperature.

In any case, extremes of temperature and humidity must be avoided.

For food contact applications, the product properties, according to the specifications, are guaranteed for 12 months after the production date.

Values are subject to change without notice.

Last update: 06/22/2022