

Description:

One-side coated paper with heat sealability properties in its back side. It's a paper packaging solution to replace heat sealing laminates.

End uses:

Flexible packaging

Print methods:

Offset, Flexo, Rotogravure

Certificates:

- [Creaset Range List of certificates](#)
- [PEFC Chain of Custody \(multisite\)](#)
- [FSC Chain of Custody \(multisite\)](#)
- [REACH regulation Lecta](#)
- [ISO 14001 Environment](#)
- [EMAS Motril mill](#)
- [ISO 50001 Energy Efficiency](#)
- [ISO 9001 Quality](#)
- [ISO 45001 Health and Safety](#)
- [ISO 22000 Food Safety - Motril](#)

For further details regarding compliance with food contact regulation, please contact our sales teams.

Technical specifications

Property	Test Method	Unit	Tolerance	70	75	80	85
Substance	ISO 536 TAPPI T410	g/m ²	± 4%	70	75	80	85
Thickness	ISO 534 TAPPI T411	µm	± 4%	62	66	70	74
Whiteness D65/10°	ISO 11475 TAPPI T562	°CIE	± 3	68	68	68	68
Opacity	ISO 2471 TAPPI T519	%	-2	85	85.5	86	86.5
Paper gloss	ISO 8254 TAPPI T480	%	± 5	65	65	65	65
Seal strength (120 °C, 0.2s, 5 bars)	ASTM D1876	2029/ N/25mm	-0,5	4.5	4.5	4.5	4.5

Values are subject to change without notice.

Last update: 02/17/2023