

Description:

Two-side clay-coated release paper for siliconization with special reverse side. Good dimensional stability and extra lay-flatness.

Generally used for graphic films applications.

End uses:

Industrial uses, RBP and film carriers

Print methods:**Certificates:**

- [Lineret CCK Duo - List of Certificates](#)
- [FSC Chain of Custody \(multisite\)](#)
- [PEFC Chain of Custody \(multisite\)](#)
- [EMAS Condat mill](#)
- [EMAS Motril mill](#)
- [ISO 14001 Environment](#)
- [ISO 50001 Energy Efficiency](#)
- [ISO 9001 Quality](#)
- [ISO 45001 Health and Safety](#)

Lineret CCK Duo

TECHNICAL DATA SHEET

Technical specifications

Property	Test Method	Unit	Tolerance	120	128	135
Substance	ISO 536 TAPPI T410	g/m ²	±4%	120	128	135
Thickness	ISO 534 TAPPI T411	µm	±4%	112	118	124
Parker roughness (top side)	ISO 8791-4 TAPPI T555	µm	≤ 2,5	2	2	2
Parker roughness (back side)	ISO 8791-4 TAPPI T555	µm	≤ 4,0	2.4	2.4	2.4
Tensile strength MD	ISO 1924-2 TAPPI T 494	kN/m	-0.7	6	6.2	6.5
Tensile strength CD	ISO 1924-2 TAPPI T 494	kN/m	-0.3	3.1	3.2	3.3
Cobb Unger (top side)	SCAN-P 37:77	g/m ²	≤0,8	0.4	0.4	0.4
Cobb Unger (back side)	SCAN-P 37:77	g/m ²	≤2.0	1.2	1.2	1.2

Values are subject to change without notice.

Last update: 07/08/2021