

Coral Book White Smooth

PRODUCT DATA SHEET

Description:

Lecta's high white uncoated woodfree paper with a smooth satin finish.

High white uncoated paper with a smooth satin finish for the publishing market, specially produced from woodfree pulp for excellent machine performance.

Designed for offset printing, guaranteed for digital laser and pre-print laser, and recommended by major digital printing press manufacturers.

Available in a wide range of substances and formats, in sheets and reels.

End uses:

Books, Brochures, Catalogues, Covers, Direct mail, Folders, Inserts, Packaging, Postcards

Print methods:

Digital, Flexo, Laser/Dry toner, Offset, Rotogravure

Certificates:

- [Packaging and Packaging Waste \(EN 13427\) - Coral Book White](#)
- [Safety of Toys \(EN 71-3\) - Coral Book Ivory](#)
- [Sensory Analysis \(EN 1230\) - Coral Book White](#)
- [Elemental Chlorine Free \(ECF\) - Coral Book](#)
- [Food Contact \(XXXVI BfR\) - Coral Book White](#)
- [Safety Data Sheet - Coral Book](#)
- [FSC Chain of Custody \(multisite\)](#)
- [PEFC Chain of Custody \(multisite\)](#)
- [EMAS Zaragoza mill](#)
- [ISO 14001](#)
- [ISO 50001 Energy Efficiency](#)
- [ISO 9001 Quality](#)
- [OHSAS 18001 \(multisite\)](#)

Technical specifications

Property	Test Method	Unit	Tolerance	70	80	90	100	120
Substance	ISO 536	g/m ²	±4%	70	80	90	100	120
Thickness	ISO 534 TAPPI T411	µm	-	63	72	80	88	102
Bulk	ISO 534 TAPPI T411	cm ³ /g	±0.03	0.90	0.90	0.89	0.88	0.85
Opacity	ISO 2471 TAPPI T519	%	-2.0	89.5	91.5	93.5	94.5	96.0
Brightness R457/D65	ISO 2470-2	%	±2	101	101	101	101	101
Whiteness D65/10°	ISO 11475	CIE	±5	143	143	143	143	143
Color a* D65/10°	TAPPI T527 ISO 5631-2	abs.	-	2.9	2.9	2.9	2.9	2.9
Color b* D65/10°	TAPPI T527 ISO 5631-2	abs.	-	-13.0	-13.0	-13.0	-13.0	-13.0
Bekk smoothness	ISO 5627	seg.	≥250	300	300	300	300	300
Cobb	ISO 535	g/m ²	±5	25	25	25	25	25
Relative humidity	TAPPI T502	%	±7	40	40	40	40	40

Storage recommendations

Coral Book White Smooth

PRODUCT DATA SHEET

Paper dimensions are very sensible to humidity variations that is why we supply paper in waterproof packaging. Once the packaging is opened, a moisture exchange can take place between the paper and the environment.

Ideally, the paper should be stocked in pressrooms conditioned to 50% (± 5) relative humidity and 23°C (± 2) temperature. In any case, extremes of temperature and humidity must be avoided.

For food contact applications, the product properties, according to the specifications, are guaranteed for 12 months after the production date.

Before starting a production run, check that the printability is correct on both sides of 30-50 sheets.

Values are subject to change without notice.

Last update: 04/29/2019